

K-Standard		20630.0005			
Issued by TLL	Authorized by MAO	Valid from 2017-02-20	Page 1(3)	Edition 1	
Oorganisk ytbehandling – metod: Alk Zink + Svartpassivering & Sealer Inorganic surface treatment – method: Alk Zinc + Black passivation & Sealer					

1 METOD

1.1 Allmänt

Alkalisk Zink + Svartpassivering & Sealer är en metod där man på elektrolytisk väg faller ut metallskiktet (zink) med efterföljande passivering på kemisk väg.

Zinkbeläggningen skyddar mot basmetallkorrosion (rödrost) och passiveringen skyddar mot vitblemma (vit korrosion på förzinkade ytor). Ett extra lager med sealer förbättrar korrosionsskyddet ytterligare.

Godkänd alternativ metod : Zink/Järn + Svartpassivering med samma skiktjocklek (12 µm) på Zinkbeläggning och utan Sealer.

2 ANVÄNDNINGSSOMRÅDEN

2.1 Allmänt

Metoden används när man vill uppnå ett gott skydd mot korrosion och samtidigt ha god kontroll på oförändrade mått- toleranser med svart kulör.

Temperaturreståndelsen är relativt god. Den korrosionsskyddande effekten påverkas inte negativt vid temperaturer upp till 150°C.

2.2 Exempel på användningsområden

Vissa detaljer har förutsättningar att vara mer lämpliga för Alkalisk Zink + Svartpassivering & Sealer än andra. Exempel:

- Detaljer med lagermonteringsytor och begränsade slitageytor, t ex kedjehjul
- Detaljer avsedda att monteras med fästelement
- Skydd mot transport- och hanteringsskador
- Korrosionsskydd

2.3 Begränsningar

Det finns detaljer som inte lämpar sig för Alkalisk Zink + Svartpassivering & Sealer. Exempel:

- Belastade rörliga delar
- Rör med krav på invändig behandling längre än dubbla innerdiametern
- Detaljer större än 2500 x 1000 x 500 mm
- Detaljer tillverkade av stål med en brottgräns $\geq 1450 \text{ N/mm}^2$

Detaljer som ska svetsas får definitivt inte ytbehandlas enligt denna K-standard före svetsning. Zink kan vid uppvärmning orsaka zinkfrossa hos den som utsätts för gaserna.

1 METOD

1.1 General

Alkaline Zinc + Black passivation & Sealer is a method where the surface treatment coating (zinc) is electrolytically precipitated following a chemically passivation.

The zinc coating protects against base metal corrosion (red rust) and the passivation protects against white rust (white corrosion on zinc surfaces). An extra layer of sealer improves the corrosion protection further more.

Approved alternative method : Zinc/Iron + Black passivation with the same thickness (12 µm) of Zinc coating and without Sealer.

2 RANGE OF APPLICATION

2.1 General

The method is suitable when the combination of good corrosion protection and unchanged measuring tolerances with black colour is desired.

The temperature resistance is relatively good. The corrosion protective effect will not be effected in a negative way in temperatures up to 150°C.

2.2 Exempel på användningsområden

Some articles are more suitable for Alkaline Zinc + Black passivation & Sealer than others. Example:

- Articles with mounting surfaces for bearings and with limited wearing surfaces, for example sprockets
- Articles intended for mounting with fasteners
- As protection against transportation and handling damages
- Corrosion protection

2.3 Limitations

There are articles not suitable for zinc/iron + Black passivation. Example:

- Loaded moving parts
- Pipes with requirements on internal surface treatment longer than twice the inner diameter
- Articles bigger than 2500 x 1000 x 500 mm
- Articles manufactured of steel with a tensile strength $\geq 1450 \text{ N/mm}^2$

Articles intended for welding may under no conditions be treated according to this K-standard before welding. At heating zinc can cause serious health problem to people exposed to the gas.

K-Standard		20630.0005			
Issued by TLL	Authorized by MAO	Valid from 2017-02-20	Page 2(3)	Edition 1	
Oorganisk ytbehandling – metod: Alk Zink + Svartpassivering & Sealer					
Inorganic surface treatment – method: Alk Zinc + Black passivation & Sealer					

3 KONSTRUKTIONASPEKTER

3.1 Konstruktionsanvisningar

Det elektrolytiskt utfärdade skiktets tjocklek är direkt beroende av elmängden som passerar detaljens yta. Strömtätheten och därmed skiktjockleken blir större på utstående delar, hörn och liknande. Däremot minskar skiktjockleken i kaviteter, inåtgående hörn osv.

En detalj som ska genomgå ytbehandlingen Alkalisk Zink + Svartpassivering & Sealer bör

- vara jämnt och enkelt utformad
- svetsas vid överlappande ytor
- utformas så att nödvändiga radier är så stora som möjligt.

3.2 Maskering

Maskering av ytor som inte skall ytbehandlas är möjlig.

3.3 Upphängning

Detaljen bör förses med lyfthål eller lyftöglor för att underlätta dopkning. Om detta inte är möjligt bör anvisning om lämpliga upphängningspunkter ges på ritningen.

4 ANGIVELSE

4.1 Angivelse på ritning

Hänvisningen till denna ytbehandlingsmetod görs med tilläggs-texten:

Oorganisk ytbehandling Kalmar K-standard 20600.0000, I3
Inorganic surface treatment

4.2 Beteckning enligt SS 147000

Fe/Zn 12/P4/T2

Fe/	Basmetall (järn eller stål)
Zn	Alkalisk Zink beläggning
12	Zink-skiktets tjocklek i µm
P4	Svart passivering
T2	Sealer

Beteckning alternativ metod (Zink/Järn + Svartpassivering):
Fe/Zn-Fe 12/P4

5 MILJÖ OCH KRAV

5.1 Krav på arbetsmiljön vid efterbearbetning

Om en detalj som ytbehandlats enligt denna K-standard måste efterbearbetas ska detta göras på en arbetsplats med ordentligt utsug. Andningsskydd med lämplig klassificering enligt riktlinjer från skyddsombud ska användas.

3 DESIGN ASPECTS

3.1 Design guidelines

The thickness of the electrolytically precipitated coatings is dependent of the electric charge passing the surface of the article. Current density and with that the coating will be thicker on outstanding parts, corners and similar. On the other hand it will be thinner in cavities, inward corners etc.

An article intended for the surface treatment Alkaline Zinc + Black passivation & sealer ought to

- be even and simple in form
- be welded at overlapping surfaces
- have as large radii as possible.

3.2 Masking

Masking for surfaces not intended for treatment can be done.

3.3 Hanging

To make dipping easier the article ought to be provided with holes or eyes for lifting. If this is not possible suitable hook up points shall be defined on drawing.

4 DESIGNATION

4.1 Designation on drawing

Reference to this surface treatment method is made by the additional text:

Oorganisk ytbehandling Kalmar K-standard 20600.0000, I3
Inorganic surface treatment

4.2 Designation according SS 147000

Fe/Zn 12/P4/T2


Fe/	Base metal (iron or steel)
Zn	Alkaline Zinc coating
12	Thickness of zinc coating in µm
P4	Black passivation
T2	Sealer

Designation alternative method (Zinc/Iron + Black passivation): Fe/Zn-Fe 12/P4

5 ENVIRONMENT AND REQUIREMENTS

5.1 Working environment when finishing treatment

If an item, surface treated according to this K-standard, needs finishing treatment, this shall be carried out in a work place with accurate evacuation system. Respiratory protective equipment with suitable classification according to guidelines from the safety representative shall be used.

K-Standard		20630.0005			
Issued by TLL	Authorized by MAO	Valid from 2017-02-20	Page 3(3)	Edition 1	
Oorganisk ytbehandling – metod: Alk Zink + Svartpassivering & Sealer Inorganic surface treatment – method: Alk Zinc + Black passivation & Sealer					

5.2 Tillverkningskrav

Se K-standard 20630.0006

5.2 Manufacturing requirements

See K-standard 20630.0006